

B. CLAIMS:

Please amend claims 2 and 7 as follows. A complete listing of all the claims appears below; this listing replaces all earlier amendments and listings of the claims.

1. (Cancelled)

2. (Currently Amended) A finished gelatin capsule ready for packaging, comprising a capsule shell formed from a capsule film having a thickness not exceeding 0.030 inches, wherein the finished capsule shell has an end composition comprising:

at least one gelatin in about 20 -55 weight % gelatin;

plasticizer in about 19-40 weight %; and

at least one hydroxypropylated, ~~substantially ungelatinized~~ starch in about 5-35 weight %, wherein the at least one hydroxypropylated starch is at least 50% ungelatinized; and

a water content of 9.5 -11.5 weight %.

3. (Previously Presented) The capsule of claim 2, wherein the plasticizer comprises at least glycerin.

4. (Previously Presented) The capsule of claim 2, wherein the plasticizer comprises at least sorbitol.

5. (Original) The capsule of claim 2, wherein the plasticizer is selected from the group consisting of polyethylene glycol, sucrose, mannitol, corn syrup, fructose, cellulose, dioctyl-sodium sulfosuccinate, triethyl citrate, tributyl citrate, 1,2-propylenglycol, mono-, di- or triacetates of glycerol, and natural gum.

6. (Previously Presented) The capsule of claim 2, wherein the at least one gelatin comprises about 25-40 weight % of the capsule.

7. (Currently Amended) The capsule of claim 2, wherein the at least one hydroxypropylated, ~~substantially ungelatinized~~ starch comprises 7-30 weight % of the capsule.

8. (Original) The capsule of claim 2, wherein the at least one gelatin is a gelatin of about 275 bloom.

9. (Original) The capsule of claim 2, wherein the at least one gelatin is a bovine gelatin.

10. (Original) The capsule of claim 2, wherein the at least one gelatin is a combination of fish and bovine gelatins.

11. (Original) The capsule of claim 2, wherein the at least one gelatin is a combination of a plurality of fish gelatins.

12. (Previously Presented) The capsule of claim 10, wherein fish gelatin comprises about 5-95 weight % and bovine gelatin comprises about 5-95 weight % of the capsule.

13. (Previously Presented) The capsule of claim 10, wherein the combination of gelatins comprises about 25-35 weight % fish gelatin and about 65-75 weight % bovine gelatin.

14. (Previously Presented) The capsule of claim 10, wherein fish gelatin comprises about 28 weight % and bovine gelatin comprises about 72 weight %.

15. (Cancelled)

16. (Previously Presented) The capsule of claim 2, wherein the capsule is formed from a capsule film having a thickness less than about 0.025 inches.

17. (Previously Presented) The capsule film of claim 2, wherein the capsule is formed from a capsule film having a thickness less than about 0.020 inches.

18. (Previously Presented) The capsule film of claim 2, wherein the capsule is formed from a capsule film having a thickness less than about 0.015 inches.

19. (Withdrawn) A process for making an edible compound for forming capsules comprising the steps of:

- a. selecting a base gelatin for the edible compound;
- b. placing the base gelatin in a temperature controlled mixing unit;
- c. adding a predetermined amount of purified water to the mixing unit to create a gel mass;
- d. maintaining the gel mass at a temperature no greater than 65°C;
- e. mixing predetermined amounts of at least one predetermined starch and a predetermined amount of at least one plasticizer in a separate vessel to create a slurry;
- f. transferring the slurry to the gel mass to create an encapsulation formulation;
- g. maintaining the formulation at temperature less than about 65°C;
- h. applying vacuum to de-aerate the formulation;
- I. transferring the formulation to a temperature controlled vessel and maintaining the temperature thereof at less than about 65°C; and
- j. transferring the formulation to a rotary die encapsulation machine for processing.

20. (Withdrawn) A rotary die gelatin encapsulation process comprising the steps of:

- a. casting at a first predetermined speed a continuous first gelatin ribbon having a first predetermined thickness on a first casting drum having a first predetermined temperature cooled to less than ambient temperature;

b. casting at a second predetermined speed a continuous second gelatin ribbon having a second predetermined thickness on a second casting drum having a second predetermined temperature cooled to less than ambient temperature;

c. uniting the first gelatin ribbon and the second gelatin ribbon to form gel pockets and injecting fill material into the gel pockets to produce freshly formed gelatin capsules; and

d. processing the freshly formed capsules to reduce surface tackiness.

21. (Withdrawn) The process of claim 20, wherein the predetermined first and second casting speed is equal to or between 2.0 and 2.5 RPM.

22. (Withdrawn) The process of claim 20, wherein the predetermined first and second casting speed is equal to or between 2.5 and 3.0 RPM.

23. (Withdrawn) The process of claim 20, wherein the predetermined first and second casting speed is equal to or between 3.0 and 3.3 RPM.

24. (Withdrawn) The process of claim 20, wherein the predetermined first and second casting speed is equal to or between 3.3 and 3.5 RPM.

25. (Withdrawn) The process of claim 20, wherein the predetermined first and second casting speed is equal to or between 3.5 and 4.5 RPM.

26. (Withdrawn) The process of claim 20, wherein the first and second predetermined thickness is less than approximately 0.030 inches.

27. (Withdrawn) The process of claim 20, wherein the first and second predetermined thickness is less than approximately 0.025 inches.

28. (Withdrawn) The process of claim 20, wherein the first and second predetermined thickness is less than approximately 0.020 inches.

29. (Withdrawn) The process of claim 20, wherein the first and second predetermined thickness is less than approximately 0.015 inches.

30. (Withdrawn) The process of claim 20, wherein the first and second predetermined temperature is less than about 12°C.

31. (Withdrawn) The process of claim 20, wherein the first and second predetermined temperature is between 8°C and 10°C.

32. (Withdrawn) The process of claim 20, wherein the cooling of the casting drums to a first and second predetermined temperature less than ambient temperature is achieved by water cooling of the drums.

33. (Withdrawn) The process of claim 20, wherein the cooling of the casting drums to a first and second predetermined temperature less than ambient temperature is achieved by air cooling of the drums.

34. (Withdrawn) The process of claim 20, wherein the step of processing the freshly formed capsules further comprises a step of drying the capsules.

35. (Withdrawn) The process of claim 20, wherein the step of processing the freshly formed capsules further comprises a step of applying a surface treatment to the capsules.

36. (Withdrawn) The process of claim 35, wherein the surface treatment further comprises at least one agent selected to enhance, complement or ameliorate some aspect of the filling of the capsule.

37. (Withdrawn) The process of claim 35, wherein the surface treatment further comprises at least one flavoring agent.

38. (Withdrawn) The process of claim 37, wherein the flavoring agent is selected to have a minimal impact on cross-linking of the gelatin in the capsule.

39. (Withdrawn) The process of claim 35, wherein the surface treatment is a dusting agent.

40. (Withdrawn) The process of claim 39, wherein the dusting agent is at least one starch.

41. (Withdrawn) The process of claim 40, wherein the at least one starch further comprises tapioca starch.